

ADD:- CHANDRA VILLA, CHAMPA NAGAR, BEAWAR – 305 901 (Raj).

**Phone**: (01462) 257523, 254657 **Email**: **vccmin@gmail.com** 

## SPECIFICATIONS OF CALCITE POWDER

	OXIDES	PERCENTAGE
0.11	210	4.00/
Silica as	$SiO_2$	1-2%
Alumina	$Al_2O_3$	<1%
Iron	$Fe_2O_3$	Traces
Calcium oxide	CaO	52-56%
Magnesium oxide	MgO	<1%
Loss on Ignition	LOI	40-45%
Soda	$Na_2O$	-
Potash	$K_2O$	-
Titanium Oxide	$TiO_2$	-
R2o3 as	$Fe_2O_3 + Al_2O_3$	<1%
Calcium	CaCO <sub>3</sub>	97-98%
Carbonate		
<b>Bulk Density</b>		1-1.5%
Brightness	Against 100% MgO	90-95%

## www.vijaychemical.in

**Disclaimer:** Under our policy of continuous product development and improvement, product attributes may change over time. All information supplied is to be used for general reference purposes only. Please contact us to obtain the most current product information.