



## Vijay Chemical Company

Delivering the Quality

**ADD:-** CHANDRA VILLA, CHAMPA NAGAR, BEAWAR – 305 901 (Raj).

**Phone :** (01462) 257523, 254657

**Email :** [vccmin@gmail.com](mailto:vccmin@gmail.com)

### SPECIFICATIONS OF CHINACLAY POWDER

	OXIDES	PERCENTAGE
Silica as	SiO <sub>2</sub>	45-47%
Alumina	Al <sub>2</sub> O <sub>3</sub>	34-37%
Iron	Fe <sub>2</sub> O <sub>3</sub>	<0.03%
Calcium Carbonate	CaCO <sub>3</sub>	Traces
Magnesium oxide	MgO	<0.2%
Loss on Ignition	LOI	10-14%
Soda	Na <sub>2</sub> O	0.2-5%
Bulk Density		0.50- 0.55gm/cc
Brightness		75-78%
Acidity	pH	7.2

[www.vijaychemical.in](http://www.vijaychemical.in)

**Disclaimer:** Under our policy of continuous product development and improvement, product attributes may change over time. All information supplied is to be used for general reference purposes only. Please contact us to obtain the most current product information.