

LABORATORY REPORT

Product Code: Bitumen 80/100

Date: October 14-2018

Test	Result	Unit	Min.	Max
Specific Gravity at 25°C	ASTM D-70	°C	1.01	1.05
Penetration at 25°C	ASTM D-5	mm	80	100
Softening Point	ASTM D-36	°C	42	52
Ductility at 25°C	ASTM D-113	Cm	100	--
Loss on Heating	ASTM D-6	%	0.5	--
Flashpoint	ASTM D-92	°C	522	--
Solubility in Trichloroethylene	ASTM D-2042	%	99	--

Best Regards,



Mr. Sai Prasad
 Managing Director