

Test report of Bentonite OCMA Grade (API Standard)

Specification	Unit	Requirement	Typical Specification
Fann @ 600 rpm		30.0 Min	45-50
Fann @ 300 rpm			30-35
Plastic Viscosity			20
Yield Point/Plastic Viscosity ratio		6 Max	4.0-4.8
Filtrate Volume	ml	16.0	15.0-15.5
Wet Screen Analysis 200 Mesh	%by Wt.	2.5 Max	1.75
Dry Mesh Passing 100 Mesh BSS	%by Wt.	98.0	98-99
Moisture	%by Wt.	12.0 Max	10-12

Yours Truly,

**For
ROYAL MINERAL**




Irfan Jat