

# DryTex PU TC90

## TWO COMPONENT POLYURETHANE BASED WATER PROOFING SYSTEM

DRYTEX PU TC 90 is a two component, polyurethane-base waterproofing membrane that apply as liquid. Component A and B are separately packed and mixing suitable amount of these two components together on site, then stirred uniformly and finally apply on the substrates. After curing reaction, it will be formed to a tough and flexible waterproofing membrane with high elasticity, suitable for applications to horizontal and vertical surfaces.



### OUTSTANDING FEATURES

- It forms a uniform, flexible and elastic seamless waterproofing membrane.
- Highly resistant to oxidation, UV light and ozone because of unique additives used in compounding it.
- Excellent mechanical and thermal resistant.
- Good Abrasion resistant.
- More durable than normal coatings and lasts longer than most other coatings.
- Superior wetting and adhesion properties ensure durable bond and resistance to peeling, chipping, and or separation and a longer life.
- It is extremely chemical resistant.
- Has the unique property of adapting itself over the irregular contours of the deck and forming a waterproof and impervious.

### FIELD OF APPLICATION

DRYTEX PU TC 90 is specially designed for waterproofing of various types of substrate Ideal waterproofing system for concrete based wet area, built up roofs, maintenance of existing roofs, masonry and concrete walls, bathrooms, basements, bridges, decks, metal surfaces etc

After curing reaction, it will be formed to a tough and flexible waterproofing membrane with high elasticity, suitable for applications to horizontal and vertical surfaces



engineered to perform

### CHARACTERISTICS (Confirms to ASTM C 836)

PROPERTIES	TYPICAL DATA	TEST METHOD
Construction	Liquid Elastomeric Polyurethane	
Tear Strength	>20 N/mm <sup>2</sup>	ASTM D 624
Tensile strength	> 4 N/mm <sup>2</sup>	ASTM D 412
Elongation	800%	ASTM D 412
Solid content	92 %	
Recovery	100%	
Adhesion on Concrete	2.5 N/mm <sup>2</sup>	
Low Temp. Flexibility	- 50 ° C	ASTM D 648
Softening point	170 ° C	ASTM D 2398
Shore A Hardness	> 60	
Crack bridging	Pass	
Permeability	0.03 perms	ASTM E 96
Coverage	1.2 L / 1 m <sup>2</sup> at 1000 micron DFT	
VOC	< 50 g/l	
Setting time	One day	
Color	Black and Grey	
Duration between the coats	4 hours	
Pot life @25° C	70 mins	

*All values given are subject to ±5-10% tolerances*

### INSTALLATION

**SURFACE PREPARATION :** Surface to be waterproofed shall be dry, clean, sound and free of all contaminants which may interfere with adhesion or proper curing .The substrates should not contain holes or cracks and should be dust-free. All shrinkage cracks shall be treated with suitable material. Moving structural cracks shall be routed out and caulked with approved ORGANIX material. Detailing like horizontal-vertical junctures ,projections, expansion joints and other areas of potential high movement may require reinforcement mate and sealants to detail. Consult with OBS tech for further information. All detailing must be cured for a minimum period of 12 hours.

**MIXING :** Component Part A and party B are separately packed and mixing suitable amount of these two components together on site , and then stirred uniformly to get have uniform liquid which to be applied on the required substrate.

**APPLICATION :** This liquid is spread at the desired thickness onto the prepared surface. The coating is applied from the container using standard roofing brushes, squeegees or rollers equipment at the recommended coverage rates on properly cleaned and prepared dry substrates. Application of the System should be done in one complete step to create a smooth uniform self leveling surface without cold joints, lines or streaks. Apply the first coat at the rate of 500 micron thickness. Let it dry fully (approximately 4-6 hours should be waited between two layers), then apply the second coat (500micron thickness) .Waiting time shortens in hot weather and lengthens in cold weather.

### PACKING

20 Litre packs (Two Pack System)

Health and Safety : DRYTEX.PU TC 90 is non-flammable, non-toxic and no health hazards.