

## Molecular Sieve Powder 4A

Property	Unit	4A	4A-D	4A-5	Note
Static H <sub>2</sub> O Adsorption	%wt	≥27.00	≥26.00	≥26.00	RH75%, 25°C
Bulk Density	g/ml	≥0.70	≥0.75	≤0.65	Tapped
Package Moisture	%wt	≤22.00	≤22.00	≤22.00	550°C, 2hr
Screen Residue	%wt	≤0.50	≤0.50	≤0.50	325 Mesh
PH Value	~	≤11.00	≤11.00	≤11.00	5% solution
D50	um	3-5	6.5-9.5	<3.00	Laser Particle Size Analyzer

### Packing:

- 40 kg/bag, and each bag has inner PE bag.
- 500 kg/bag, 600 kg/bag, 1000 kg/bag, and each bag has coating.
- Other packing according to your requirement.

