

Boss Reclaim Rubber Private Limited

At. Chanchavadarda, Ta. Maliya, Dist. Morbi , Gujarat, India

Natural Reclaim - Natural

Sr.	Properties	Unit of Measurement	Testing Method	Specification
1	Acetone Extract	%	ISO 1407	11 $\pm$ 4
2	ASH Contain	%	ISO 247	25 $\pm$ 4
3	Carbon Black	%	ISO 1408	20 $\pm$ 7
4	Volatile Matter	%	ISO 248	1 Max
5	RHC by Difference	%	By Difference	47 Min.
6	Elongation at break	%	ISO 37, ISO/DTS 16095	230 Min.
7	Hardness (Shore A)	-	ISO 7619	60 $\pm$ 5
8	Mooney Viscosity ML (1+4) at 100°C		ASTM D1646	30 $\pm$ 15
9	Specific Gravity	Gm/CC	ISO 2781	1.25 $\pm$ 0.05
10	Tensile Strength	Kg/cm ²	ISO 37, ISO/DTS 16095	35 Min