



1070LA17

LOW DENSITY POLYETHYLENE

FOR EXTRUSION COATING AND FILM APPLICATIONS

1070LA17 is an extrusion coating grade Low density Polyethylene (LDPE) produced by high pressure autoclave process. This grade is specially developed for extrusion coating on different substrates and contains no additives. It exhibits excellent drawdown characteristics maintaining good adhesion, with very low neck-in even at high line speeds. It can also be easily processed into thin gauge films for adhesive lamination and heat and pressure lamination.

Typical Characteristics*			
Property	Test Method	Unit	Typical Value**
Melt Flow Index (190°C/2.16 kg)	ASTM D1238	gm/10min	8.5
Density (23°C)	ASTM D1505	gm/cc	0.917
Tensile Strength at Break (MD/TD)	ASTM D882	MPa	18/15
Elongation at Break (MD/TD)	ASTM D882	%	250/400

* Typical characteristics and not to be taken as specifications

** Typical properties measured on 40 µm blown film made with 1.0 mm die gap & 2.0 BUR

APPLICATIONS

Extrusion coating, heat & pressure lamination film.

Typical Process Conditions:

- Typical Process Temp (°C) - 200 – 320

Regulatory Information

- Meets the requirements stipulated in standard IS: 10146 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to IS 16738:2018 "Positive List of Constituents for Polypropylene, Polyethylene and their Copolymers for its Safe Use in Contact with Foodstuffs and Pharmaceuticals"
- The grade and the additives incorporated in it also comply with the FDA: CFR Title 21, 177.1520, Olefin polymers.
- 1070LA17 is not intended for use in medical and pharmaceutical applications.

Storage Recommendations

- Bags should be stored in dry/closed conditions at temperatures below 50 °C and protected from UV / direct sunlight.

DISCLAIMER

The information contained herein may include typical properties and processing parameters of the grade or its typical performances when used in respective applications. The values given above are based on analysis of representative samples and not the actual product supplied. It is the customer's responsibility to inspect and test our grades in order to satisfy itself as to the suitability of the products for customers' particular application. The customer is solely responsible for all determinations regarding any use of material or product and any process in its area of interest. RIL assumes no obligation or liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of using any of the information or product given in this document. The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or otherwise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorized agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.