

❖ Product Description

- | | |
|---|---|
| <ul style="list-style-type: none"> I. Low carbon, high manganese and 1/2molybdenum electrode II. Specially coated with surface lubricant to remove any wire contaminant | <ul style="list-style-type: none"> III. Contact tip life increases as compared with non-copper coated wire alternative IV. Specially for high tensile steels V. Controlled chemistry |
|---|---|

❖ Range of Application

- | | |
|---|--|
| <ul style="list-style-type: none"> I. For welding of beams in structures II. For fabrication of cylinders and vessels | <ul style="list-style-type: none"> III. Welding of pressure vessels and shipyards IV. Common carbon steels |
|---|--|

❖ Classification

- AWS/SFA 5.23 EA 4

❖ % Chemical Composition

Type Of Wire		C	Mn	S	Si	P	Cr	Cu	Mo
EA 4	Min	0.05	1.20	-	-	-	-	-	0.45
	Max	0.15	1.70	0.025	0.20	0.025	-	0.35	0.65

❖ Wire Size & Welding Position

- | | |
|--|---|
| <ul style="list-style-type: none"> • Diameter in mm- 0.60, 0.80, 0.90, 1.00, 1.20, 1.40, 1.60 | <ul style="list-style-type: none"> • Weld Position- All position |
|--|---|

❖ Packaging

- 25kg coil with or without support

Special Notes: -

- (1) All the value above mentioned are typical values.
- (2) Usually all chemistry and mechanical properties will depend on actual wire chemistry and arc voltage used for welding.

SHAKUNT ENTERPRISES PRIVATE LIMITED

Corporate Office: - 619/A, EMMAR DIGITAL GREEN, 6th Floor, Sector-61, GURUGRAM (HARYANA)-122102

E-Mail:- info@shakunt.com

Ludhiana Works:- B-XXIX-595/5,Campa Cola Road,Dhandari Kalan Industrial Area-C,Ludhiana (PUNJAB) [INDIA](#)

Dharwad Works:- Plot no.577 C & D,Belur Industrial Area,Dharwad-580011 (KARNATAKA) [INDIA](#)

Vadodara Works:- 67-A,G.I.D.C,Majusar,Savli,Vadodara-397115 (GUJARAT) [INDIA](#)