

SPECIFICATION OF API 13-A SEC.-9 DRILLING GRADE BENTONITE POWDER

SR.NO.	PARAMETERS	SPECIFICATION
1	Suspension Properties Viscometer dial reading @ 600 rpm	30 Minimum
2	Yield point/plastic viscosity ratio	3 Maximum
3	Filtrate volume / Filter loss	15 cm ³ Maximum
4	Residue of diameter greater than 75 micron	4% Maximum
5	Moisture	12% Maximum